



# TABLA TEMPERATURA VS: PRESIÓN

## FACTOR DE CORRECCIÓN

TEMPERATURA		PVC	CPVC	PPL
°F	°C			
70°	21.09°	100%	100%	100%
80°	26.64°	90%	96%	97%
90°	32.19°	75%	82%	91%
100°	32.74°	62%	85%	85%
110°	43.29°	50%	77%	80%
115°	46.07°	45%	74%	77%
120°	48.84°	40%	70%	75%
125°	51.62°	35%	66%	71%
130°	54.39°	30%	62%	68%
140°	60.00°	22%	55%	65%
150°	65.49°	---	47%	57%
160°	71.04°	---	40%	50%
170°	76.59°	---	32%	26%
180°	82.14°	---	25%	---
200°	93.24°	---	18%	---
210°	98.79°	---	15%	---